

TECHNICAL DATA SHEET

FASTEC EPDM FOAM PROFILED FILLER BLOCK

Profiled Filler Blocks serve to seal cavities between profiled sheeting and adjacent materials or substrates, such as flashings. They are manufactured to order, to your exact requirements, and are available in a wide range of combinations and variations.

TECHNICAL DATA FOR EPDM FOAM MATERIAL

| | Test Method | Test Result |
|----------------------------------|-------------|-------------|
| Density (kg/m ³) | ISO 845 | 48 |
| Shore hardness (00 Scale) | IE-08 | 42 |
| Cell size (mm) | IE-09 | ≤0.35 |
| Elongation at break (%) | ISO 1926 | 300 |
| Tensile strength (kPa) | ISO 1926 | 224 |
| Compression strength (kPa) | ISO 844 | |
| 10% | | 20 |
| 25% | | 35 |
| 50% | | 79 |
| Compression set (%) | ISO 1856B | |
| After 30 min | | 8 |
| After 24 hours | | 2 |
| Maximum working temperature (°C) | IE-02 | 70 |

This information is given to the best of our knowledge. All test data are average values and should be considered as guidelines only.

ADDRESS

Catford Road
Roundthorn Industrial Estate
Manchester, M23 9LR

ONLINE

www.fastecfixings.com
sales@fastecfixings.com

PHONE

0161 945 1440